

**13.X-05 ON THE MODULATED MAGNETIC STRUCTURE OF CeAl<sub>2</sub>** By B. Barbara, IBM T. J. Watson Research Center, Yorktown Heights, New York and Laboratoire Louis Néel C.N.R.S. 166X 38042, Grenoble; J. L. Buevos, I.L.L. 156X, 38042, Grenoble; M. F. Rossignol, Laboratoire Louis Néel C.N.R.S., 166X 38042, Grenoble; J. X. Boucherle and J. Schweizer, D.R.F./D.N. - C.E.N.G. 85X 38041 Grenoble and I.L.L. 156X 38042, Grenoble, and C. Vettier, I.L.L. 156X, 38042 Grenoble.

The intermetallic Laves-phase compound CeAl<sub>2</sub> exhibits sinusoidally modulated magnetic structure with the propagation vector  $\vec{q}_1 = 1/2 + \tau, 1/2 - \tau, 1/2$  (B. Barbara, J. X. Boucherle, J. L. Buevos, M. F. Rossignol, J. Schweizer, Sol. State Comm. 24, 481, 1977). There are twenty-four non-equivalent  $\vec{q}_1$  vectors in the Brillouin zone which lead to a twenty-four-component order parameter. The existence of small magnetic peaks with  $\vec{q}_c = (1/2, 1/2, 1/2)$  and the continuous character of the magnetic ordering transition suggest a coupling between different  $\vec{q}_1$  vectors (S. M. Shapiro, E. Guerwitz, R. D. Parks, L. C. Kupferberg, Phys. Rev. Lett. 43, 1748 (1979)). On the other hand the increase of diffracted intensity at some points of the reciprocal lattice and the correlative decrease at other points (under small uniaxial stress at  $T \approx T_n/2$ ) suggest a single  $\vec{q}$  magnetic structure with an overall cubic symmetry restored by the coexistence of twenty-four magnetic domains (B. Barbara, J. X. Boucherle, M. F. Rossignol, C. Vettier, Phys. Rev. Lett. 45, 11, 1980).

These two points as well as the evolution of the incommensurate magnetic structure of CeAl<sub>2</sub> under hydrostatic pressure will be discussed. Furthermore the fact that such modulated structures involving moment reductions characterize the ground state of a Kramers ion will be related to the ordered Kondo lattice model.

**13.X-06 MAGNETIC PHASE TRANSITIONS IN SUPERCONDUCTORS** By J. W. Lynn, Department of Physics and Institute for Physical Science and Technology, University of Maryland\*, College Park, Maryland 20742, and National Measurement Laboratory, National Bureau of Standards, Washington, D.C. 20234.

The rare-earth (RE) ternary superconductors belonging to the REMo<sub>6</sub>X<sub>8</sub> (X=S, Se) and RERh<sub>4</sub>B<sub>4</sub> classes of materials have provided the first unambiguous examples of the coexistence of superconductivity and long range magnetic order. For systems in which the interactions between rare-earth moments are antiferromagnetic in nature, the magnetic order only weakly perturbs the superconductivity since there is no macroscopic magnetization associated with the magnetic state. There are now a rather large number of ternary materials which exhibit long-range antiferromagnetic order coexisting with superconductivity over a wide range of temperatures. The competitive nature of these two cooperative phenomena is illustrated for systems which display ferromagnetic interactions, such as HoMo<sub>6</sub>S<sub>8</sub> and (Er<sub>1-x</sub>Ho<sub>x</sub>)Rh<sub>4</sub>B<sub>4</sub>, which first become superconducting at a temperature T<sub>C1</sub> and then order magnetically at lower temperatures. At first the superconductivity is able to prevent ferromagnetic alignment, and a compromise long-wavelength oscillatory magnetization is established at intermediate temperatures. At sufficiently low temperatures, however, the superconductivity is destroyed (at T<sub>C2</sub>) as ferromagnetism sets in. A similar reentrant superconducting transition has recently been found in ErRh<sub>1.1</sub>Sn<sub>3.6</sub>, although in this case the ferromagnetic order appears not to be truly long range in nature. The behavior of these reentrant ferromagnets contrasts with the pseudo-binary substitutional alloy systems such as (Ce<sub>1-x</sub>RE<sub>x</sub>)Ru<sub>2</sub>, where rather long-range ferromagnetic correlations develop in the superconducting state, but true long range magnetic

order only appears above the percolation threshold where the superconducting state is fully suppressed.

Inelastic neutron scattering studies have shown that the crystal field splittings of the rare-earth ions in these materials are large in comparison with the magnetic energies, as might be expected since the magnetic ordering temperatures are typically below 1 K. Consequently the nature of the magnetic state at low temperatures and its influence on the superconducting properties is dictated in each case by the crystal field ground state of the 4f electrons rather than the free-ion properties. The crystal field results obtained to date on these materials will also be reviewed.

\*Work supported by the NSF, DMR 79-00908.

**13.X-07 ANISOTROPIC AND ANHARMONIC INTERACTIONS IN CUBIC AB<sub>3</sub> INTERMETALLIC COMPOUNDS.** By J. Faber, Jr. and G. H. Lander, Argonne National Laboratory, Argonne, Illinois, P. J. Brown, Institute Laue Langevin, Grenoble, France, A. Delapalme, Laboratoire Leon Brillouin, Gif-sur-Yvette, France, C.-K. Loong and C. Stassis, Iowa State University, Ames, Iowa.

The usual assumptions for cubic solids are that the atoms vibrate isotropically and harmonically. However, the recognition that bonding effects play an important role in determining the properties of solids, and the observation that solids expand contradict these assumptions. It is precisely the higher-order corrections to these approximations that give us information about bonding and the restoring potentials associated with atom vibrations. Here we report the results of single crystal neutron Bragg scattering studies on the intermetallic compounds UGe<sub>3</sub>, USn<sub>3</sub>, URh<sub>3</sub>, URu<sub>3</sub>, CeSn<sub>3</sub> and AuCu<sub>3</sub>. In the temperature range, 80 < T < 600 K, these crystals exhibit the ordered cubic Pm3m structure (O<sub>h</sub><sup>1</sup>). Both strong fundamental and weak superlattice reflections have been measured out to high Q = 4π sinθ/λ (Q < 15 Å<sup>-1</sup>) values. Large anisotropies in the superlattice intensities are observed that cannot be explained in the harmonic approximation. However, the point group symmetry for the B atoms in AB<sub>3</sub> is tetragonal (D<sub>4h</sub>), and an anisotropic potential well is anticipated. The effects of anisotropic (but harmonic) thermal motion are enormous, e.g., in CeSn<sub>3</sub> the thermal vibration ellipsoid is 1.6 times as extended along the unique tetragonal axis as compared with perpendicular to it. We will show that the detailed shape of the thermal vibration ellipsoid is sensitively dependent upon the outer electron configuration at the B atom site, thus reflecting p-type bonding for Ge or Sn, but d-type bonding for Rh or Ru. Information about these