

08.5-7 MAGNETIC ORDERING IN THE NATURAL ORTHOPYROXENE $\text{Fe}_{0.87}\text{Mg}_{0.13}\text{SiO}_3$. By A. Wiedenmann^{a)}, J.R. Regnard^{a)} and S.S. Hafner^{b)}.

a) DRF. CENG 85X F-38041 Grenoble, b) University Marburg, Marburg, F.R.G.

In the crystal structure of orthopyroxene $\text{Fe}_x\text{Mg}_{1-x}\text{SiO}_3$ two nonequivalent positions M_1 and M_2 of oxygen octahedra are occupied by Fe^{2+} and Mg^{2+} with a preference of Fe^{2+} for the more distorted M_2 site. In the unit cell edge sharing octahedra build up four ribbons of infinite length along the c axis well separated from each other ($d = 4.9 \text{ \AA}$). Each ribbon consists of two linear chains of M_2 which enclose a zigzag chain of M_1 (Virgo and Hafner, Amer. Mineral. (1970) 55, 201). Investigations of the magnetic properties of the natural pyroxene $\text{Fe}_{0.87}\text{Mg}_{0.13}\text{SiO}_3$ were performed on a polycrystalline sample of 100 mg. The powder susceptibility follows a Curie-Weiss law with $\Theta_p = 34 \text{ K}$ and $\mu_{\text{eff}} = 5.24 \mu_B$, indicating large orbital contributions. χ exhibits an inflection point at $T_N = 26 \text{ K}$ reflecting an antiferromagnetic ordering. The onset of long range magnetic order at T_N was confirmed by neutron diffraction. The propagation vector is $\vec{k} = [000]$ indicative for a collinear magnetic structure. From an intensity refinement the coupling between the 16 sublattices was obtained: all the moments within a ribbon are aligned ferromagnetically along the b axis with an antiferromagnetic coupling between neighbouring ribbons. The ferromagnetic exchange interaction between the nearest neighbours within the ribbons ($d = 3.1 \text{ \AA}$) is certainly much stronger than the antiferromagnetic coupling of the moments between neighbouring ribbons, giving rise to a special type of 1D magnetic behaviour. Mössbauer experiments in the paramagnetic region revealed two distinct quadrupole interactions of Fe^{2+} of 3.0 and 1.99 mm/s for the sites M_1 and M_2 , respectively. Below the transition temperature the hyperfine spectra (with large linewidth of about 0.8 mm/s) are well described by a distribution of distinct electric field gradients and magnetic hyperfine fields due to the different Mg^{2+} , Fe^{2+} configurations surrounding M_1 and M_2 as nearest neighbours.

08.6-1 ESR AND MÖSSBAUER STUDIES OF Cu- AND Fe-CONTAINING SULFOSALTS. By K.Bente, V.Kupcik, Min.-Krist.Institut Univ. Göttingen, G.Amthauer, Institut f. Miner. und Krist. Univ. Marburg, D.Siebert, Phys.Chem. Institut Univ. Freiburg

ESR and Mössbauer studies were carried out on the Cu- and Fe-containing sulfosalts kobellite ((Cu,Fe)Pb₆Sb₂Bi₄S₁₆), Cu_{8.4}Fe_{1.2}Bi_{10.8}S₂₂, covellite (CuS), idaite (Cu₅FeS₆), and Cu₄Bi₄S₉, which contain lacks of positive charge basing on Cu⁺, Pb⁺⁺, Sb⁺⁺⁺, Bi⁺⁺⁺, Fe⁺⁺, S²⁻ and S₂²⁻ (if covellite fragments are present). The phases were synthesized under condensed conditions using the elements (99.999%) as starting materials. For the synthesis of the phases containing Fe in minor amounts, Fe enriched in ⁵⁷Fe was used. The ESR and Mössbauer studies were performed from room temperature to the temperature of liquid nitrogen (LN₂).

The ESR studies gave no Cu⁺⁺ signals for covellite over the whole temperature range and Cu⁺⁺ signals for Cu₄Bi₄S₉ at $T \leq 173 \text{ K}$ ($q=1.91$) and for idaite at $T \leq 96 \text{ K}$ ($q=1.87$). Because of the charge balance of these phases, mixed valence state of Cu ($\sim 1.5+$) has to be suggested at temperatures without an ESR signal. This suggestion is verified in the case of idaite showing mixed valence state for Fe ($\sim 2.5+$) by Mössbauer studies with an isomer shift of $\delta = 0.35$ for tetrahedrally coordinated Fe. ESR studies on the phases kobellite and Cu_{8.4}Fe_{1.2}Bi_{10.8}S₂₂ show paramagnetic signals for Cu⁺⁺ over the whole temperature range with $q=2.01$ and 2.019 respectively.

Mössbauer studies lead to Fe⁺⁺ in both cases. An empirical term for the mixed valence state and/or the valence of 2+ for Cu in positive charge deficient sulfosalts is proposed.