

11.4-11 DIFFUSE X-RAY SCATTERING OF NaTl SINGLE CRYSTALS. By J. Schneider  
Institut für Kristallographie und Mineralogie  
Universität München, D-8000 München

Non rotating monochromatic single crystal x-ray (NOROMOSIC) investigations of the Zintl-phase intermetallic compound NaTl were undertaken for the first time. They show unusual and temperature dependent diffuse patterns. In addition to anisotropic thermal diffuse scattering close to Bragg peaks, extended off-Bragg regions of diffuse scattering are observed. (Fig.1)

The interpretation is performed on the basis of lattice dynamical models which assume weak bonding of adjacent [110] zig-zag chains consisting of Na and Tl atoms respectively.




Fig.1  
NOROMOSIC x-ray  
pattern of NaTl  
single crystal  
[110]-axis

11.4-12 THE TEMPERATURE DEPENDENCE OF THERMAL VIBRATIONS IN OXYGEN-OCTAHERAL FERROELECTRICS. By S.A.Ivanov, G.B.Ter-Mikaelyan, V.E.Zavodnik and Yu.N.Venevtsev.  
L.Ya.Karpov Institute of Physical Chemistry,  
Moscow, USSR.

The study of the character of thermal vibrations is the important part in the dynamics of crystal lattice and is of principal value in the clearing up the nature and real mechanisms of many physical phenomena in ferroelectrics. Taking the above into consideration the temperature dependence of thermal vibrations  $U^2$  for several ion sublattices is observed for a number of polycrystalline samples with perovskite and pyrochlore structures in the wide temperature range. The kind of obtained dependences of  $U^2(T)$  allowed in the some cases to make certain conclusions about the presence of the anharmonicity of the vibrations of some ions and thereby to consider them to be ferroelectrically active. In the case of  $\text{KTaO}_3$  the particularities of thermal vibrations of ions were also defined with very high accuracy with the help of the precise X-ray experiment which was carried out on the perfect single crystal. The results obtained by this experiment on the whole confirmed the qualitative conclusions which were made in the course of studying the polycrystalline samples of  $\text{KTaO}_3$ . The analysis of the further possibilities of studying of the anharmonicity of the thermal vibrations on polycrystalline samples and single crystals of the above mentioned structural families was made.

11.4-13 THERMODYNAMIC FUNCTIONS FOR SULFUR FROM CRYSTAL STRUCTURE AND LATTICE DYNAMICS.

By C.M.Gramaccioli, Earth Science Department and G.Filippini, Physical Chemistry Department University of Milan, I-20133 Milan, Italy

From the X-ray diffraction data on orthorhombic sulfur (Abrahams, *Acta Cryst.* (1955) 8,662; Pawley & Rinaldi, *Acta Cryst.* (1972) B28,3605) a suitable model for lattice-dynamical calculations has been derived, using the Born-von Kármán procedure, and a non-rigid molecular model (Gramaccioli & Filippini, *Acta Cryst.* (1983) A39,784). The van der Waals force field has been taken from Rinaldi & Pawley (*J.Phys.C* (1975) 8,599), and the internal force field was initially taken from Steudel & Mäusel (*Z.Naturforsch.* (1978) 33a,951). The difference between the calculated and the observed values for the lowest internal frequencies are however high if a rigid model is assumed, as it was in previous calculations of thermodynamic functions for the vapour phase, where the influence of packing in the crystal upon internal frequencies was neglected (Guthrie *et al.*, *J.Amer.Chem.Soc.* (1954) 76,1488): this involves differences of about 2 cal/mole. $^{\circ}\text{K}$  for entropy at room temperature, which are much larger than other corrections for existence of several molecular species. Because of this, the internal field has been modified by essentially lowering the torsional constants. From these calculations, a satisfactory agreement is obtained for vibrational frequencies, and an excellent match with experimental data is obtained for thermodynamic functions in the crystal and temperature factors.

11.5-1 LATERAL AND ANGULAR PARAMETERS OF THE UNIT-CELL OF A HIGHLY PURE SILICON CRYSTAL. By H. Siebert and P. Becker, Physikalisch-Technische Bundesanstalt, Braunschweig, Federal Republic of Germany.

The redetermination of the Avogadro constant currently in progress at the Physikalisch-Technische Bundesanstalt requires a relative uncertainty of less than  $5 \times 10^{-7}$  in the determination of the unit-cell volume in a silicon single crystal. From precision measurements of lattice spacings (Ando, Bailey, Hart, *Acta Cryst.* (1978) A 34,484) it is known that the shape of the unit-cell, even in highly pure silicon crystals, is not exactly cubic. Thus the unit-cell volume, calculated from the knowledge of only one lattice plane spacing may exhibit a systematic error of up to  $\Delta v/v \approx 1 \times 10^{-6}$ .

Using a whole set  $\{h k l\}$  of equivalent lattice planes with  $\sqrt{h^2 + k^2 + l^2} = \text{const.}$ , the axial lengths  $a, b, c$ , axial angles  $\alpha, \beta, \gamma$  and the volume  $v$  of a "real" unit-cell were calculated, assuming that the unit-cell is slightly deformed by internal or external forces.

By crystal-to-crystal comparison measurements, relative aberrations from the cubic shape in the order of  $\pm 2 \times 10^{-7}$  were found. The results are listed in the Table. In order to study the differences in lattice plane spacings, thin crystal wafers in a double crystal arrangement and consecutive Laue reflections were used. Provided both wafers were of almost the same thickness, the rocking curves show a detailed fine structure which allows the differences in angular position to be detected to better than  $10^{-8}$  rad.

In future work the mean unit-cell volume of a cube of silicon one kilogram in weight will be determined. Further investigation will be aimed at clarifying whether, as Ando, Bailey and Hart have surmised, the unit-cell volume in a highly pure silicon crystal remains almost