

**s11.m3.p1** **Microstructures of Polygonal Serpentes from HRTEM Imaging, Electron Diffraction, and Simulation Data.** B. Devouard (1), A. Baronnet (2), (1) *Université Blaise Pascal, UMR-CNRS 6524, 5 rue Kessler, F-63038 Clermont-Fd, France,* (2) *CRMC2-CNRS, Campus de Luminy, Case 913, F-13288 Marseille, France.*  
Keywords: mineralogical crystallography, electron crystallography, mineralogy.

Serpentes are layered silicates of ideal formula  $Mg_3Si_2O_5(OH)_4$ . Because of a missfit between the tetrahedral and octahedral sub-layers of the structure, they can display an extreme variety of flat, rolled, or modulated microstructures. Polygonal serpentes are tubular fibers with a polygonal section, each of the 15 or 30 sectors showing a flat, lizardite-like, structure. High resolution transmission electron microscopy (HRTEM) imaging, selected area electron diffraction (SAED) and simulations of the diffraction patterns are combined to further document the microstructures of the most widespread types of polygonal serpentes. The SAED simulations were obtained by numerical Fourier transforms of computer-generated Bravais-cell images of fiber sections.

Imaging, diffraction and simulation data are in agreement with a model involving lateral continuity of the layered structure and a curvature (without inversion of the tetrahedral sheets) across the sector boundaries. This model is based on the one proposed by Baronnet *et al.*<sup>1</sup>, and differs from sharp-boundary models by Chisholm<sup>2, 3</sup> (without inversion) and by Dodony<sup>4, 5</sup> (with inversion). Easy plastic deformation of fibrils with hollow cores suggests that glissile dislocation walls occupy sector boundaries. HRTEM imaging and SAED reveal that the stacking sequences of the layers in adjacent sectors are homogeneously sheared by  $b/3$ , for 30-sectored fibers as well as 15-sectored ones. Axial fivefold symmetry is confirmed for polygonal serpentes.

Streaked diffraction chords connecting Bragg's reflections are typical of any polygonal fibril. They are due to curved layers with constant curvature at sector boundaries, involving extra spacing and distorted H-bonds between the layers. This would be a peculiarity of polygonal serpentes compared to other rolled serpentine varieties.

[1] Baronnet, A.; Mellini, M.; Devouard, B.: Sectors of polygonal serpentine. A model based on dislocations. *Phys. Chem. Minerals*, (1994), 21:330-343.

[2] Chisholm, J.E.: Geometrical constrains on the growth of sectors in polygonal serpentine. *J. Phys. D : Appl. Phys.*, (1991), 24:199-202.

[3] Chisholm, J.E.: The number of sectors in polygonal serpentine. *Can. Mineral.*, (1992), 30:355-365.

[4] Dodony, I.: Microstructures in serpentinites. *Microscopia Elettronica*, (1993), 14(Suppl.):249-252.

[5] Dodony, I.: Structure of the 30-sectored polygonal serpentine. A model based on TEM and SAED studies. *Phys. Chem. Minerals*, (1997), 24:39-49.