

[1] Chandra P., et al., *Phys. Rev. Lett.*, 1990, **64**, 88. [2] Capriotti L., *Int. J. of Mod. Phys. B*, 2001, **15**, 1799. [3] Millet P., et al., *Mater. Res. Bull.*, 1998, **33**, 1339. [4] Melzi R., et al., *Phys. Rev. Lett.*, 2000, **85**, 1318. [5] Melzi R., et al., *Phys. Rev. B*, 2001, **64**, 024409. [6] Eick H. A., et al., *Acta Chem. Scand.*, 1966, **20**, 722. [7] Bombardi A., et al., *Phys. Rev. Lett.*, 2005, submitted.

**Keywords:** lattice anomalies, square lattice, frustration

#### P.11.01.10

*Acta Cryst.* (2005). A61, C387

#### Comparison and Analysis of the Samples with Same Synthesis of Bi-Sr-Ca-Cu-O, Prepared by Different Ways of Heating

Basilis Papadopoulos<sup>1</sup>, C. Stergiou<sup>2</sup>, A. Stergiou<sup>1</sup>, <sup>1</sup>Department of Physics, <sup>2</sup>Department of Electrical & Computer Engineering, Aristotle University of Thessaloniki (A.U.Th.). Thessaloniki, Greece. E-mail: stergiou@auth.gr

For the study of superconducting materials, produced by different ways of heating, five mixtures with proportions 2:2:2:3 of Bi<sub>2</sub>O<sub>3</sub>, SrCO<sub>3</sub>, CaCO<sub>3</sub>, CuO were prepared. The four of them were heated, directly, at 860°, 870°, 880° and 890° C, individually, while the last one, gradually, at the same temperatures. All the samples were heated in free atmosphere, for 48h.

The crystalline phases, created in the eight cases, were studied by XRD measurements and characterized, using the PDF2 database. Further, the Powder Profile Analysis (Rietveld's method) was used for the crystallographic study of the samples. The phase Bi<sub>2</sub>CaSr<sub>2</sub>Cu<sub>2</sub>O<sub>8</sub>, with space group A<sub>maa</sub> and mean unit cell parameters a=5.4028, b=5.3923 c=30.6559 [1], was the main phase for all the samples, with a percentage greater than 80%. Some other phases with percentage 5-15% for the different samples were defined, say the Bi<sub>2</sub>SrCuO<sub>5</sub>, with structure analogous of Dy<sub>2</sub>BaCuO<sub>5</sub> [2] (Pnma space group and mean unit cell parameters a=12.2020, b=5.6732, c=7.1357).

Results of the samples synthesis for each of the processes were discussed.

[1] Petricek V., Gao Y., Lee P., Coppens P., *Powder Diffraction*, 1994, **9**, 28-37. [2] Salinas-Sanchez A., Garcia-Munoz J.L., Rodriguez-Carvajal J., Saez-Puche R., Martinez J.L., *J. of Solid State Chemistry*, 1992, **100**, 201-211.

**Keywords:** superconductors, crystal structure, Rietveld's method

#### P.11.01.11

*Acta Cryst.* (2005). A61, C387

#### Crystallographic Study of Superconducting series Nd<sub>1+x</sub>Ba<sub>2-x</sub>Cu<sub>3</sub>O<sub>y</sub> (x=0.0, 0.2, 0.4, 0.6), Prepared at 850°C and 860°C

C. Stergiou<sup>1</sup>, G. Voutsas<sup>2</sup>, A. Stergiou<sup>2</sup>, <sup>1</sup>Department of Electrical & Computer Engineering, <sup>2</sup>Department of Physics, Aristotle University of Thessaloniki, Thessaloniki, Greece. E-mail: stergiou@auth.gr

The structural properties of superconducting series Nd<sub>1+x</sub>Ba<sub>2-x</sub>Cu<sub>3</sub>O<sub>y</sub> (x=0.0, 0.2, 0.4, 0.6), prepared at 850°C and 860°C, were studied. For this aim, four powder mixtures with suitable proportions of Nd<sub>2</sub>O<sub>3</sub>, BaO and CuO were prepared and heated at temperature 850° and next the produced samples were reheated at 860°C, in free atmosphere for 48h, in both cases. The creation and the evolution of the phases, as a function of the quantity x, was studied by analysis of XRD measurements. The phase characterization was realized with a suitable program, using the PDF2 data-base. Farther, the Powder Profile Analysis (Rietveld's method) was used for the phase structure refinement and the exact determination of the phase percentages. Four crystal phases, NdBa<sub>2</sub>Cu<sub>3</sub>O<sub>7</sub> [1], Nd<sub>2</sub>BaCuO<sub>5</sub> [2], BaCuO<sub>2</sub> [3] and CuO [4], were defined for the samples prepared at 850°C, while only the first three of these were defined for the samples prepared at 860°C. The creation and percentages of the crystal phases in the samples were discussed, as a function of the temperature and the quantity x.

[1] Lundqvist P., Rapp O., Tellgren R., Bryntse I., *B-Condensed Matter*, 1997, **56**, 2824. [2] Schiffler S., Mueller-Buschbaum H., *Monatshfte fuer Chemie und verwandte Teile anderer Wissenschaften*, 1986, **117**, 465. [3] Kipka R., Mueller-Buschbaum H., *Zeitschrift fuer Naturforschung, Teil B., Anorganische Chemie, Organische Chemie*, 1977, **32**, 121. [4] Asbrink S., Norrby L.J., *Acta Cryst. B*, 1970, **26**, 8.

**Keywords:** superconductors, crystal structure, Rietveld's method

#### P.11.01.12

*Acta Cryst.* (2005). A61, C387

**Crystallographic Study of Samples Produced from Mixtures La<sub>1+x</sub>Ba<sub>2-x</sub>Cu<sub>3</sub>O<sub>y</sub> (x=0.0, 0.2, 0.4, 0.6), Heated at 850°C and 860°C**  
Semir Yilmaz<sup>1</sup>, C. Stergiou<sup>2</sup>, A. Stergiou<sup>1</sup>, <sup>1</sup>Department of Physics, <sup>2</sup>Department of Electrical & Computer Engineering, Aristotle University of Thessaloniki. Thessaloniki, Greece. E-mail: stergiou@auth.gr

Four powder mixtures with suitable proportions of La<sub>2</sub>O<sub>3</sub>, BaO and CuO according to general type La<sub>1+x</sub>Ba<sub>2-x</sub>Cu<sub>3</sub>O<sub>y</sub> (x=0.0, 0.2, 0.4, 0.6), were prepared and heated at temperature 850° and next the produced samples were reheated at 860°C, in free atmosphere for 48h, in both cases.

The creation and the evolution of the phases, as a function of the quantity x, was studied by analysis of XRD measurements. The phase characterization was realized with a suitable program, using the PDF2 data-base. Farther, the Powder Profile Analysis (Rietveld's method) was used for the phase structure refinement and the exact determination of the phase percentages.

Three crystal phases (the superconducting La<sub>1.76</sub>Ba<sub>0.24</sub>CuO<sub>4</sub> [1] and LaBa<sub>2</sub>Cu<sub>3</sub>O<sub>7</sub> [2], and the non superconducting BaCuO<sub>2</sub> [3]), were defined for all the samples. The creation and percentages of the crystal phases in the samples were discussed, as a function of the temperature and the quantity x.

[1] Katano S., Fernandez-Baca J.A., Funahashi S., Mori N., Ueda Y., Koga K., *Physica C*, 1993, **214**, 64. [2] Skakle J.M.S., West A.R., *Physica C*, 1994, **227**, 336. [3] Kipka R., Mueller-Buschbaum H., *Zeitschrift fuer Naturforschung, Teil B., Anorganische Chemie, Organische Chemie*, 1977, **32**, 121.

**Keywords:** superconductors, crystal structure, Rietveld's method

#### P.11.03.1

*Acta Cryst.* (2005). A61, C387

#### Growth and Structural Investigations on lead-doped NdMnO<sub>3</sub> Single Crystals

H.L. Bhat<sup>a</sup>, Nilotpal Ghosh<sup>a</sup>, Suja Elizabeth<sup>a</sup>, G. Nalin<sup>b</sup>, B. Muktha<sup>b</sup>, T.N. Guru Row<sup>b</sup>, <sup>a</sup>Department of Physics, Indian Institute of Science, Bangalore-560012, India. <sup>b</sup>Solid State and Structural Chemistry Unit, Indian Institute of Science, Bangalore-560012, India. E-mail: hlbhat@physics.iisc.ernet.in

Single crystals of Nd<sub>(1-x)</sub>Pb<sub>(x)</sub>MnO<sub>3</sub> with different dopant concentrations were grown by high temperature solution growth technique using PbO-PbF<sub>2</sub> flux [1]. Electron diffraction patterns showed the presence of superlattice structure x=0.25 and above. The structure of Nd<sub>(1-x)</sub>Pb<sub>(x)</sub>MnO<sub>3</sub> crystals were determined by single crystal x-ray diffraction for two different x values using a Bruker AXS Smart Apex CCD diffractometer with MoK $\alpha$  radiation. Positional co-ordinates of Nd and Mn atoms were obtained by SHELXS97 and refined by SHELXL97. Substitution of Pb at Nd site results in structural change from tetragonal (x=0.25) to cubic (x=0.38) lattice. The lattice parameters of tetragonal and cubic unit cells are a = b = 7.725(1)Å, c = 3.884(1) Å and a = b = c = 7.737(2) Å respectively. While the unit cell volume of tetragonal structure (P4/mmm) is comparable to that of parent NdMnO<sub>3</sub>, the volume of cubic unit cell (Pm3m) is doubled. The static distortion of MnO<sub>6</sub> octahedra is maximum for parent orthorhombic NdMnO<sub>3</sub> (x = 0). The mismatch between different Mn - O bond lengths of Nd<sub>1-x</sub>Pb<sub>x</sub>MnO<sub>3</sub> is much less at x = 0.25 and 0.38. The MnO<sub>6</sub> octahedral distortion and inter octahedral tilt are removed progressively with higher doping. Changes in transport properties as a function of temperature at different doping levels are in accordance with the structural changes.

[1] Ghosh N., Elizabeth S., Bhat H.L., Subanna G.N., Sahana M., *Journal of Magnetism and Magnetic Materials*, 2003, **256**, 286-292.

**Keywords:** crystal growth, crystal structure, magnetic materials

#### P.11.03.2

*Acta Cryst.* (2005). A61, C387-C388

#### Atomic Image of Diluted Magnetic Semiconductor Zn<sub>1-x</sub>Mn<sub>x</sub>Te Obtained by X-ray Fluorescence Holography

Shinya Hosokawa<sup>a</sup>, Naohisa Happo<sup>b</sup>, Kouichi Hayashi<sup>c</sup>, Toru Ozaki<sup>a</sup>,

<sup>a</sup>Faculty of Engineering, Hiroshima Institute of Technology. <sup>b</sup>Faculty of Information Sciences, Hiroshima City University. <sup>c</sup>Institute for Materials Research, Tohoku University, Japan. E-mail: hosokawa@cc.it-hiroshima.ac.jp

From an X-ray diffraction [1], the lattice constant of diluted magnetic semiconductor  $Zn_{1-x}Mn_xTe$  linearly changes with varying  $x$  (Vegard's law), while an XAFS results [2] showed almost unchanged Mn-Te and Zn-Te bond lengths (Pauling's rule). This discrepancy led to a question of how the large the large  $MnTe_4$  tetrahedra can be squeezed into the small  $ZnTe_4$  lattice.

X-ray fluorescence holography (XFH) is a new technique that allows one to investigate a three-dimensional local image around a specific element. The sample was irradiated by intense X-rays of certain energies beyond the Mn K absorption edge at BL37XU/SPring-8 in order to obtain the Mn  $K_{\alpha}$  fluorescence hologram [3]. A three-dimensional atomic image around the Mn central atoms was derived from the hologram using Barton's algorithm. The nearest- and third-nearest-neighbour Te atoms were clearly visualized. However, the second-nearest-neighbour Zn or Mn atoms are barely visible in this image due probably to a highly distorted cation Zn(Mn) sub-lattice.

[1] Yorder-Short D.R., et al., *J. Appl. Phys.*, 1985, **58**, 4056. [2] Hoppo N., et al., *J. Phys.:Condens. Matter*, 1996, **8**, 4315. [3] Hosokawa S., et al., *Jpn. J. Appl. Phys.*, 2005, **44**, 1011.

**Keywords:** three-dimensional image reconstruction, X-ray fluorescence spectroscopy, magnetic semiconductors

#### P.11.03.3

*Acta Cryst.* (2005). A61, C388

#### Investigation of $LaMn_{2-x}Fe_xSi_2$ ( $0 \leq x \leq 1.2$ ) by Magnetic Measurements and Neutron Diffraction

Yalcin Elerman<sup>a</sup>, Ayhan Elmali<sup>a</sup>, Ilker Dincer<sup>a</sup>, Helmut Ehrenberg<sup>b</sup>, Hartmut Fuess<sup>b</sup>, Aziz Daoud-Aladine<sup>c</sup>, <sup>a</sup>Engineering Physics, Ankara University, TR-06100 Besevler-Ankara, Turkey. <sup>b</sup>Institute for Materials Science, Darmstadt University of Technology, Petersenstrasse 23, D-64287 Darmstadt, Germany. <sup>c</sup>Laboratory for Neutron Scattering, ETHZ & PSI, CH-5232 Villigen, Switzerland. E-mail: elerman@ankara.edu.tr

The various magnetic structures and phase transitions in the  $LaMn_{2-x}Fe_xSi_2$  system have been thoroughly studied by X-ray powder diffraction, magnetic measurements and powder neutron diffraction. The substitution of Fe for Mn leads to a decrease in the lattice parameters and the magnetic interactions in the Mn sublattice cross over from a ferromagnetic character to an antiferromagnetic one. The magnetic structures of the  $LaMn_{2-x}Fe_xSi_2$  compounds with  $x = 0.2, 0.475, 0.5, 0.7$  and  $1.0$  have been determined between 2 and 450 K by neutron diffraction. A typical  $SmMn_2Ge_2$ -like magnetic behavior is observed for the  $x = 0.475$  sample. The magnetic phase transition from ferromagnetism to antiferromagnetism for this sample occurs at the intralayer Mn-Mn distance  $d_{Mn-Mn} = 2.89 \text{ \AA}$ . This value exceeds the well known corresponding threshold value  $d_{Mn-Mn} = 2.87 \text{ \AA}$  in the pure Mn  $RMn_2X_2$  compounds [1-2]. The results are summarized in the  $LaMn_{2-x}Fe_xSi_2$  magnetic phase diagram [3].

[1] Elerman Y., Dincer I., Elmali A., Ehrenberg E., Fuess H., Duman E., Acet M., *J. Phys.: Condens. Mater.*, 2004, **16**, 405. [2] Duman E., Acet M., Dincer I., Elmali A., Elerman Y., *J. magn. Magn. Mater.*, 2004, **272-276**, 529. [3] Dincer I., Elmali A., Elerman Y., Ehrenberg E., Fuess H., Daoud-Aladine A., *J. Phys.: Condens. Mater.*, 2005, in press.

**Keywords:** rare-earth manganese silicides, layered structure, neutron diffraction

#### P.11.03.4

*Acta Cryst.* (2005). A61, C388

#### Structural Reasons for the Giant Oxygen Isotope Effect in $Re_{0.5}Sr_{0.5}MnO_3$ Perovskites

Anatoly Balagurov<sup>a</sup>, Ivan Bobrikov<sup>a</sup>, Vladimir Pomjakushin<sup>b</sup>, Natalia Babushkina<sup>c</sup>, Oleg Gorbenko<sup>d</sup>, Anrej Kaul<sup>d</sup>, <sup>a</sup>FLNP JINR, Dubna, Russia. <sup>b</sup>LNS ETH&PSI, Villigen, Switzerland. <sup>c</sup>"Kurchatov Institute", Moscow, Russia. <sup>d</sup>Moscow State University, Moscow,

Russia. E-mail: bala@nf.jinr.ru

The giant oxygen isotope effect (a metal-insulator transition induced by  $^{16}O$  for  $^{18}O$  substitution) has been recently discovered in  $Sm_{1-x}Sr_xMnO_3$  compound for  $x$  close to 0.5 [1]. We performed a neutron diffraction study for elucidating structural reasons of this transition. Both crystal and magnetic structures have been determined for several compositions with  $Re=Sm$  and  $(Nd_{1-y}Tb_y)$ ,  $y=0.228$  and  $0.456$ . These particular (Nd/Tb) ratios were chosen to model the average ionic radii of Sm and  $(Sm_{0.5}Nd_{0.5})$  compositions respectively. In all studied samples the coexistence of ferromagnetic-metallic (FMM) and antiferromagnetic-insulating (AFMI) phases has been found at low temperature. From structural point of view both phases have the same  $Pnma$ -type structure but with strong difference in lattice parameters. The  $d(x^2-y^2)$  orbital ordering in A-type AFMI phase leads to the huge shortening of Mn-O1 distances ( $\approx 1.2\%$ ) (as well as of  $b$  lattice parameter) and stimulates strong intragranular strains, which stabilize phase separated state. The same situation, though with different type of magnetic and orbital ordering in AFMI phase, has been found in LPCM-y type manganites, which also exhibit the giant oxygen isotope effect [2].

[1] Babushkina N.A. et al., *Phys. Rev. B*, 2003, **67**, R100410. [2] Balagurov A.M. et al., *Phys. Rev. B*, 2001, **64**, 024420.

**Keywords:** manganites, neutron diffraction, isotope effect

#### P.11.05.1

*Acta Cryst.* (2005). A61, C388

#### X-ray Study of the Native Solid Hydrocarbons Transformation

Olga V. Kovaleva<sup>a</sup>, U.M. Korolev<sup>b</sup>, <sup>a</sup>Institute of Geology, Komi Science Centre, Uralian Branch of RAS, Syktyvkar, Komi Republic, Russia. <sup>b</sup>Institute of Petrochemical Synthesis of RAS, Moscow, Russia. E-mail: OlgaKovaleva@geo.komisc.ru

The subject of our investigation the native hydrocarbons (bitumens), which we defines as organic compounds with a primarily hydrocarbon basis. In the structural relation bitumens are characterized by the supermolecular organization with the sizes of elements from tens nanometers up to micron. The X-ray method opens new possible in the diagnostics of complex systems, using as numerical index a graphitization degree (Sg), which allows to diagnose as well as follow the dynamics and transformation mechanism of bitumens in the carbonization series: asphalt – asphaltite – kerite – anthraxolite – graphite.

The purpose of the research work is to study X-ray transformation of bitumens on the supermolecular level. The X-ray spectrum of bitumens of different transformation stages consist of two basic reflection 0.48 and 0.38 nm corresponding to the hydrocarbon polynaphtenic phase ( $N_T$ ) and an amorphous graphite-like phase ( $G_T$ ). The concentration of the latter increase with the growth of the catagenetic transformations degree. That is a final transformation product of natural bitumen is graphite. This testify to the single ransformation mechanism of natural bitumens. Thus, the X-ray methods allow to determine the genetic type of native organic substances and establish the catagenetic transformation level of the organic substances.

[1] Korolev U.M., *Solid Fuel Chemistry*, 1995, 99-111.

**Keywords:** X-ray diffraction and structure, hydrocarbons, nanostructures

#### P.11.05.2

*Acta Cryst.* (2005). A61, C388-C389

#### The Influence of Synthesis Conditions on the Packing of the Spherical Particles of Silica in a Supramolecular Structure

Dmitry V. Kamashev, Institute of Geology, Komi Science Centre, Uralian Branch, Russian Academy of Science, Syktyvkar, Russia. E-mail: kamashev@geo.komisc.ru

As a result of the conducted experiments on the synthesis and precipitation of monodisperse spherical silica particles (100-800 nm) in different conditions we have determined a direct relationship between the packing type of particles and pH, water concentration,