

samples with zirconium the texture components are sharper.

The above findings were more or less confirmed by the EBSD analysis. The analysis of the deformed and recrystallized parts indicate the changes from deformed part after one pass to about 70% recrystallized fraction after four and eight passes.

The work is a part of the research programs MSM 00216208 34.

MS46 P06

Structural and ferroelectric characteristics in the Ba(Ti_{1-x}Zr_x)Li_{xy}O_{3(1-xy)}F_{3xy} solid solution K. Taïbi^a, A. Kerfah^a, A. Guehria-Laidoudi^a, A. Simon^b and J. Ravez^b
^aFaculté de Chimie, U.S.T.H.B., BP 32 El-Alia, Bab-Ezzouar, Alger, Algeria. ^bI.C.M.C.B.-C.N.R.S., 87 avenue D' A. Schweitzer, 33608 Pessac, France.
 E-mail: datakam@yahoo.fr

Keywords: lead-free, ferroelectric, transition

Relaxor are a special class of ferroelectrics with very interesting properties. Relaxor materials actually used are lead-based ceramics which present a disadvantage due to the toxicity of PbO. The actual evolution of research is oriented to environment-friendly application. In this way, we have previously investigated new lead free compositions. Dielectric studies performed on Ba(Ti_{1-x}Zr_x)Li_{xy}O_{3(1-xy)}F_{3xy} solid solutions showed three kinds of behaviour. For compositions very close to BaTiO₃ the three phase transition were retained as was the case in the classical ferroelectric BaTiO₃. For compositions Ba(Ti_{1-x}Li_x)O_{3(1-x)}F_{3x} and Ba(Ti_{1-x}Zr_x)O₃, it appears one broad peak with frequency dispersion characteristic of relaxor behaviour. For compositions close to Ba(Ti_{1-x}Zr_x)O₃ only one diffuse phase transition, without frequency dispersion was evidenced. In this latest domain, it is possible to observe the spontaneous phase transition from ferroelectric to relaxor state just by thermal change.

To understand the origin of this behaviour much works based on structural and physical models are performed. It has been found that the frequency and the temperature T_m can be described by using the Vogel-Fulcher relationship [3, 4]. In the present work we fitted all the dielectric data to this Vogel-Fulcher equation and correlated the results with structural data obtained by powder diffraction study. The fitting parameters and the upper limit of the composition for ceramics with relaxor state were defined. The plot of T_m(f)/T_m (1 kHz) versus the logarithm of the frequency allows to determine the limit of composition between the ferroelectric and the relaxor state which is close to 0.155.

Powder XRD patterns indicates a particular behaviour for y = 0.25 where two kinds of single domain phases are observed: tetragonal, for 0 ≤ x < 0.15 and cubic for 0.15 ≤ x ≤ 0.25. The latest domain corresponds to the relaxor phase. The change from tetragonal to cubic symmetry related to the disappearance of the (200) and the appearance of the (111) reflexions, characteristic of the cubic perovskite structure. The relaxor to normal ferroelectric transformation and the structural phase transition are strongly related to the domain morphology evolution. The presence of a local disorder related to nanoscale heterogeneities is responsible of the relaxor behaviour when the composition deviates from the well known BaTiO₃ [3, 4].

[1] D.W. Viehland, S.J. Jang and L.E. Cross, *J. Appl. Phys.*, 1990, 68, 2916

[2] A.E. Glazounov and A.K. Tagantsev, *Appl. Phys. Lett.*, 1998, 73, 856.

[3] Aliouane, A. Guehria-Laidoudi, A. Simon, J. Ravez. *Solid State Sciences*, 2005, 7, 1324

[4] A. Kerfah, K. Taïbi, A. Guehria-Laidoudi, A. Simon and J. Ravez, *Solid State Sciences*, 2006, 8, 613.

MS46 P07

Structural studies of crystallization and growth of magnetron deposited TiO₂ thin films by X-ray diffraction and reflectivity Kužel Radomir, Zdeněk Matěj^a, Jan Šícha^b, Jindřich Musil^b, ^aDepartment of Condensed Matter Physics, Faculty of Mathematics and Physics, Charles University in Prague, Ke Karlovu 5, 121 16 Praha 2, Czech Republic, ^bDepartment of Physics, Faculty of Applied Sciences, University of West Bohemia in Pilsen, Czech Republic. E-mail : nichtova@gmail.com

Keywords: thin films; TiO₂, anatase; dc magnetron sputtering; microstructure

TiO₂ films are nowadays widely used because of their interesting photocatalytic and self cleaning properties. Complex X-ray scattering studies were performed on sets of titanium dioxide thin films sputtered by dual dc magnetron [1]. Three sets of nanocrystalline and amorphous TiO₂ thin films magnetron deposited on glass and silicon substrates have been studied. Phase analysis and X-ray line broadening were studied by X-ray powder diffraction in parallel beam optics; the residual stresses were measured with the aid of the Eulerian cradle and surface roughness determined by X-ray reflectivity measurement. Microstructure parameters were extracted from XRD measurements by individual peak profile fitting and also by whole powder pattern modelling [2] approach (MAUD [3], modified FOX[4]).

By both thickness dependence of XRD patterns of nanocrystalline films and depth profiling measurements it was found that rutile phase growths on the substrate and it is transformed to anatase with increasing distance from the substrate. This may be caused by temperature gradient during deposition. Another set of amorphous films with different thickness was studied after annealing and also by in-situ measurements during the heating.

It was found that the crystallization temperature started at about 250 °C for thicker films but it was higher for thinner films (< 200 nm) and reached about 350 °C. Thinner films were single phase (anatase) while thicker films above 1200 nm contained also a small amount of nanocrystalline rutile. The crystallite size of these samples immediately after crystallization was larger than 100 nm by contrast to the nanocrystalline films which did not show any significant changes after annealing in this temperature range and their crystallites remain small under about 10 nm. Annealing at temperatures above 500 °C leads to increase of crystallite size and transformation of anatase into rutile.

Simple uniaxial tensile stress and only a weak texture were found for the amorphous films after crystallization. Only for the thinnest films (~ 100 nm), the 101 texture (anatase) was found. In case of nanocrystalline films the stress was low but complicated. This can be related to significantly stronger and more complicated texture due to dual magnetron geometry.

- [1] J. Musil, D. Heřman, J. Šícha (2006). *J. Vac. Sci. Technol.* A24(3), 521-528.
 [2] P. Scardi, M. Leoni (2002). *Acta Cryst. A* 58, 190-200.
 [3] L. Lutterotti, www.ing.unitn.it/~maud.
 [4] objcryst.sourceforge.net.

The work is a part of the research programs MSM 0021620834 and MSM 4977751302 financed by the Ministry of Education of the Czech Republic and also supported by Grant Agency of the Czech Republic (106/06/0327).

MS46 P08

The powder diffractometer of beamline CRISTAL at synchrotron SOLEIL E. Elkaim^a, F. Legrand^a, G. Guillet^b, H. Mezière^c, S. Ravy^a ^aSynchrotron SOLEIL Gif-sur Yvette, France ^bLaboratoire de Physique des Solides, Orsay, France. ^cSciences Chimiques, Rennes, France. E-mail: erik.elkaim@synchrotron-soleil.fr

Keywords: powder, diffractometry, instrument development, powder x-ray diffraction.

Cristal at synchrotron Soleil, is an undulator beamline dedicated to diffraction experiments in the energy range 5-30 keV. It is equipped with 3 diffractometers suitable for most diffraction experiments (powders, single crystals, etc...).

This poster focuses mainly on the powder diffractometer which will start operating at the end of this year. This 2-circles diffractometer built by SMP[1] will be equipped with a 21-crystals multianalyser[2] for high angular resolution experiments. The large dimensions of the instrument will permit studies of samples under various conditions (low temperatures, high temperatures, etc...) with a sample environment carrying capacity of about 60kg on the inner circle.

A particular care has been taken to achieve high precision for this instrument and measurements of the accuracy will be shown. Main characteristics of the diffractometer will be given together with a description of the multianalyser.

[1] SMP Lyon, France

[2] J.-L. Hodeau, P. Bordet, M. Anne, A. Prat, A. N. Fitch, E. Dooryhee, G. Vaughan, and A. Freund, Nine crystal multianalyser stage for high-resolution powder diffraction between 6 and 40 keV, *SPIE Proceedings*, 3448, 353-361 (1998).

MS46 P09

Kinetics of the precipitation in an AZ91 alloy through in situ Xray diffraction analysis Hiba Azzeddine, Saida Abdessameud, Baya Allili & Djamel Bradai, Faculty of Physics, USTHB, BP 32 El-Alia, Dar El Beida, Algiers, Algeria. E-mail: bradai_djamel@yahoo.fr

Keywords: AZ91, Xray diffraction, discontinuous precipitation

Magnesium's good properties, such as low density (1.74 g cm⁻³) and high specific strength, make its alloys potential candidates for replacing steel and other heavier materials [1]. AZ91 is the standard magnesium die-casting alloy, being used in approximately 90% of all magnesium products [2]. The alloy AZ91 can be thought of as being based on the binary magnesium-aluminium system. From the phase diagram this system exhibit a good age hardening response but in reality the relative hardness increase is not so important when compared to the Al-Zn one. The cause of this weak hardness response is the occurrence of both the continuous and discontinuous precipitation reactions. While the first reaction is known to harden the material, the second is responsible of its softening. Discontinuous precipitation lead to a duplex cellular structure of a lamellar Mg₁₇Al₁₂ precipitate and a depleted solid solution from the supersaturated one. The continuous precipitation within the grains also consists of the equilibrium Mg₁₇Al₁₂ phase that is incoherent plate shaped (Widmanstätten structure) precipitates parallel to the basal plane of the magnesium matrix.

During the last decades, There are several reports describing the microstructures and mechanical properties of AZ91 alloys processed differently (See [3]). Some of these investigations have generally used fairly complex alloy systems where the presence of substantial alloying additions leads to the widespread dispersion of intermetallic precipitates. However very little work has been devoted to the determination of the macroscopic kinetics of the discontinuous reaction in important industrial alloys such as AZ91. In this work, we present the results of an extensive in situ determination of the kinetics of the DP reaction through Xray diffraction analysis. The results show a good agreement with a previous work in a model binary system [4].

[1] del Valle J. A., Pérez-Prado M.T. & Ruano O.A., *Mat. Sci. & Eng.*, A355 (2003) 68.

[2] Bettles C. J., Humble P. & Nie J.F., in *Proceedings of the "Third International Magnesium Conference"*, Institute of Metals (1997) pp403-417.

[3] in "Magnesium-Science, Technology and Applications, Proceedings of the "International Conference on Magnesium-Science, Technology and Applications", China (2004). Eds. W.Ke, E.H. Han, Y.F. Han, K. Kainer and A.A. Luo, *Mat. Sci. For.*, Vols. 488-489 (2004).

[4] Duly D., Brechet Y. & Chenal B., *Acta metal. Mat.*, Vol 40 N° 9 (1992). pp. 2289-2300