

Microsymposium

MS26.O04

Electric polarization from spiral order below 200K in multiferroic YBaCuFeO5

M. Morin¹, D. Scheptyakov², L. Keller², J. Rodríguez-Carvajal³, A. Scaramucci⁴, N. Spaldin⁴, M. Kenzelmann¹, E. Pomjakushina¹, K. Conder¹, M. Medarde¹

¹Paul Scherrer Institut, Laboratory for Developments and Methods, Villigen PSI, Switzerland, ²Paul Scherrer Institut, Laboratory for Neutron Scattering, Villigen PSI, Switzerland, ³Institut Laue-Langevin, Grenoble, France, ⁴ETH Zurich, Materials Theory, Zurich, Switzerland

Ferroelectric materials have been known for almost one century [1]. While their potential for applications was rapidly recognized, the possibility of combining ferroelectricity with magnetic order -preferably with ferromagnetism- has resulted in an enormous deal of interest during the last decade. Several new materials combining both types of order have been recently reported, although their promising multifunctionalities have been obscured by two facts: on one side, most of them are antiferromagnetic; on the other, their transition temperatures, typically below 40K, are too low for most practical applications. The oxygen-deficient double perovskite YBaFeCuO5 constitutes a remarkable exception. Spontaneous electric polarization has been recently reported to exist below an unusually high temperature of $T_C \approx 200\text{K}$ [2] coinciding with the occurrence of a commensurate - to - incommensurate reorientation of the Fe³⁺ and Cu²⁺ magnetic moments [3,4]. From a more fundamental point of view the observation of incommensurate magnetic order in a tetragonal material at such high temperatures is rather surprising. In particular, the nature of the relevant competing magnetic interactions and its possible link to low dimensionality or geometrical frustration is not understood at present. Although the existence of the spin reorientation in this material is known since 1995 [3] the low temperature magnetic structure has not yet been solved. Using neutron powder diffraction we have recently been able to propose a spiral model which satisfactorily describes the measured magnetic intensities below T_C . Further, investigation of the crystal structure showed the existence of small anomalies in the lattice parameters and some interatomic distances at T_C . The relevance of these findings for the magnetoelectric coupling, the direction of the polarization, the modification of the different exchange paths in the structure and the stabilization of the incommensurate magnetic order below T_C is discussed.

[1] J. Valasek *Physical Review* 15, 537(1920), [2] B. Kundys et al., *Appl. Phys. Lett.* 94, 072506, (2009)., [3] V. Caignaert et al., *J. Solid State Chem.* 114, 24, (1995).

Keywords: Multiferroic, Spiral magnetic order, Neutron diffraction